



RIGITONE® MIX 600ML

Rigitone Mix is a ready filler for Rigitone perforated plasterboard joints. It forms part of the Rigitone Ready Mix Set and is used in the Joint Filling Technique.

CHARACTERISTICS

- No mixing
- Easy to sand
- Low weight, specifically for ceiling work
- Quick tool cleaning

PROCESSING

- Insert Rigitone Mix 600ml sausage into the Rigitone Pistol and cut off the seal. Screw the Rigitone nozzle onto the adapter, then screw the adapter tightly onto the Rigitone Pistol.
- Fill the joints generously and completely so that the filler just starts to exude from the reverse of the board.
- Slightly overfill the screw heads using the Rigitone screw head template.
- Once the Rigitone Mix 600ml has begun to harden, remove any excess carefully using the Rigitone scraper and then pass the scraper back over the joints in the other direction to smooth the surface.
- The joints and covered screw heads can be sanded after a minimum of 24 hours.
- Further finishing work may be continued once the Rigitone Mix 600ml has fully dried.

TECHNICAL DATA

Designation	Rigitone Mix 600ml		
Material	Finishing compound	Type 4A	as per EN 13963: 2014
Package size	Sausage	600ml	
Processing	Material consumption	approx. 80 ml/m ²	
	Yield	600ml = approx. 7-8 m ²	
	Processing time	approx. 60 minutes	
	Processing temperature	5 to 35°C	
	Drying time	12 - 24 hours	
Storage	Store in a location which is dry and free from frost. Rigitone Mix will retain its outstanding properties for at least 6 months. Reseal opened bags well and use up promptly.		

The values given in this product data sheet solely describe the performance characteristics of the products.

T: 800 GYPROC (497762) UAE TOLL FREE

T: +971 (0)4 814 3666 INTERNATIONAL

www.gyproc.ae

First Edition

Literature Code: 334-PLT

